
PRODUCT RANGE

AGRICULTURE




... we make better polymers

LUCOBIT AG
the **EBA** Company
(Ethylene-Butyl-Acrylate)

GRADE			TYPE	COLOR	PARTICLE SIZE	GENERAL DATA		MECHANICAL DATA				WATER ABSORPTION	PH VALUE 1 % BY WEIGHT IN WATER	MONOMER CONTENT	KALIUM CONTENT	APPLICATION	OTHERS
						BA-CONTENT	DENSITY AT 23°C	TENSILE STRENGTH AT BREAK, (MD/TD)	ELONGATION AT BREAK (MD/TD)	MELT INDEX (MFI, 190°C/2,16 KG)	MELTING POINT (°C)						
						%	KG/M ³	MPA	%	G/10 MIN	°C						
						INTERNAL	ISO 1183	ISO 527-2	ISO 527-2	ISO 1133	ISO 3146						
Application	Plastics in agriculture	Lucofin 2033 DS	EBA	natural	granules	3	923	25/25	500/700	0,3	-	-	-	-	-		
		Lucofin 2133 VS	EBA	natural	granules	13	925	20/22	570/600	0,3	101	-	-	-	-		
		Lucofin 1083 DN	EBA	natural	granules	8	924	25/26	680/710	0,35	-	-	-	-	-		
	Plant growth	Lucoplant 205x	-	white	up to 5,00	-	0,56	8,0	770	-	-	≥ 350	6-7,5	≤ 500	≤ 17,8		
		Lucoplant 220x	-	white	up to 0,20-0,80	-	0,56	14,0	700	-	-	≥ 350	6-7,5	≤ 500	≤ 17,8		
		Lucoplant 230x	-	white	up to 0,30-1,00	-	0,56	12,0	800	-	-	≥ 350	6-7,5	≤ 500	≤ 17,8		

LOCATIONS



LUCOBIT Aktiengesellschaft
Basell Polyolefine GmbH / Brühler Str. 60 • B100
D-50389 Wesseling
Phone +49 2236 / 37859-0
Fax +49 2236 / 37859-99
info@lucobit.de
www.lucobit.com

Note

The information provided in this document is based on our product tests and present technical knowledge. It does not release purchasers from the responsibility of carrying out their receiving inspections. Neither does it imply any binding assurance of suitability of our products for a particular purpose. As LUCOBIT cannot anticipate or control the many different conditions under which this product may be processed and used this information does not relieve processors from their own tests and investigations. Any proprietary rights as well as existing legislation shall be observed.