

Product Data Sheet

Lucogrid®Glass120

1. Product description

Lucogrid®Glass120 is a pre-bitumized asphalt reinforcement that can be applied to the entire area or intermittently.

The tensile strength is 120 kN/m.

2. Fields of application

Durable mending of existing roads (to prevent and to fix cracks caused by excessive strain, temperature differences etc.). Can easily be incorporated into new roads for the prevention of cracks over an extended period of time.

3. Attributes

Lucogrid®Glass50 adheres perfectly to the previously applied emulsion due to the pre-bituminization. On the top side of Lucogrid®Glass120 are grated lattices to ensure immediate trafficability for construction-site traffic.

4. Processing

- Milling of the asphalt
- Proper cleaning of the milling surface
- Application of the bituminous emulsion
- mechanical installation of Lucogrid®Glass120 or
- manual installation of Lucogrid®Glass120
- Application of the top asphalt layer (thickness of at least 3.5 cm)

5. Delivery form

- Standard sizes of Lucogrid®Glass120 are rolls in widths of 0.97m (30kg), and 1.95m (60kg).
- The roll length is 50m.
- The rolls are packed individually.

Technical Data*		Main direction (MD)	Cross direction (CD)
Character	Unit	Value	Value
Appearance	-	Black grid	
Width of roll	m	0.97 / 1.95	
Length of roll	m	50	
Weight of area	g / m ²	600	
Tack coat	g/m ²	250 - 500 bituminous emulsion	
Basic glass grid	Unit	Value	Value
Overlapping	cm	10 - 15	30 - 40
Tensile modulus fiber	N/mm ²	≥ 73.000	≥ 73.000
Elongation at break	%	≤ 3,0	≤ 3,0
Fiber cross section	mm ² /m	46 50 fiber strands	48 52 fiber strands
Tensile force at 2.6%	kN/m	120	120
*These standard values are typical values and should not be regarded as specifications.			

Disclaimer: The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications; and we do not support its use for such applications. To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. However, we do not assume any liability whatsoever for the accuracy and completeness of these information. LUCOBIT AG gives no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal uses as well as the appropriate processing and handling of our products. No liability can be accepted with respect to the use of LUCOBIT AG products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any other third party materials.