

Product Data Sheet

Lucopren® EP1505-55

1. Product description

Lucopren® EP1505-55 is a thermoplastic elastomer. Due to its chemical structure, Lucopren® EP1505-55 exhibits unique properties combining the performance of a conventional elastomer with the processability of a thermoplastic polymer.

2. Product advantages

- easy processing with standard processing equipment
- flexibility
- good mechanical properties: high temperature resistant
- environmentally friendly

3. Applications

Lucopren® EP1505-55 is used primarily for injection moulding applications.

4. Processing

Lucopren® EP1505-55 is suited for conventional standard processing equipment. We recommend the following standard values for extrusion:

For injection moulding Lucopren® EP1505-55 is processed at melt temperatures ranging from 180 - 230°C and mould temperatures from 30 - 60°C.

5. Chemical resistance

Lucopren® EP1505-55 is resistant to water and aqueous solutions, salt as well as to dilute acids and bases. When exposed to aliphatic, aromatic and halogen substituted hydrocarbons, Lucopren® EP1505-55 may swell or dissolve to some degree.

6. Packaging

Granules in 20 kg aluminium-bags, standard pallet 1.000 kg.

7. Storage

Lucopren® EP1505-55 should be stored in dry conditions at a temperature below 40°C. In order to protect packaging, exposure to (UV-)light should be avoided.

Storage time over 6 months may have negative effects on product processability. We strongly recommend converting the material latest within 6 months after delivery.

Used after the recommended shelf-life, the product should be inspected according to quality assurance measures to ensure product performance.

Otherwise, product degradation may occur resulting in odour generation and colour changes.

Disclaimer: The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications; and we do not support its use for such applications. To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. However, we do not assume any liability whatsoever for the accuracy and completeness of these information. LUCOBIT AG gives no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal uses as well as the appropriate processing and handling of our products. No liability can be accepted with respect to the use of LUCOBIT AG products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any other third party materials.

Product Data Sheet

Lucopren[®] EP1505-55

Technical data			
	Standard	Unit	Standard value*
Density (23 °C)	ISO 1183	g/cm ³	0,93
Shore hardness A	DIN EN ISO 868	-	60
Tensile stress**: 23°C, 2,00mm	DIN 53504	MPa	5,10
Tensile elongation**: 23°C, 2,00mm	DIN 53504	%	730
Compression set: 70°C, 22h)	DIN 815	%	42
* These standard values are typical values and should not be regarded as specification			
** Typ 2, 200mm/min			

Processing information		
Injection moulding	Standard value*	Unit
Drying temperature	80	°C
Drying time	3	h
Process temperature	180-230	°C
Mould temperature	30-60	°C

Disclaimer: The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications; and we do not support its use for such applications. To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. However, we do not assume any liability whatsoever for the accuracy and completeness of these information. LUCOBIT AG gives no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal uses as well as the appropriate processing and handling of our products. No liability can be accepted with respect to the use of LUCOBIT AG products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any other third party materials.